


SEAM SLIPPAGE

ISO 13936-2



Principle

Seam slippage test – measures the fabric's movement at the seam slippage (mainly for upholstery fabrics).

The fabric samples are sewn together both in the warp and weft direction. The fabric is then pulled from both sides to 180N and then released to 5N. The opening of the seam where the two fabric pieces are sewn is then measured.

Results

A seam slippage of maximum 4mm is acceptable for upholstery fabrics.

Application Standards

ISO 13936-2

